

BOAFANG™

SS11E


1 SEASON


FIELD COMPOSTABLE AUTO STAPLE STRAP.
MILD STRENGTH FOR DEVELOPING TREE AND
VINE STEMS, VEGETABLE & BERRY TRAINING

*CAPABLE OF LARGER DIAMETERS THAN WIRE
TIE GUNS.*

DESIGNED TO BE LEFT IN THE FIELDS



CLAY + PAPER = 

VINYL + PLASTIC = ~~~~

KEY FEATURES


- Tie composts to soil in approximately 1 year most conditions.
- Can be applied loose or tight.
- Made from renewable and renewed resources.
- Engineered environmentally friendly replacement to toxic vinyl tape, psa tapes, wire ties.
- Low Wind and dry environment.
- Eliminates end of season collection of tie trash
- Roll bundle is just at 2 kg for 10 rolls, this is 0.18 kg per roll.
- Increase the plant area because of its high efficiency.
- Maintains integrity in sunny and wet applications.
- Entirely U.S. materials, innovation and manufactured




TENSILE STRENGTH TESTING



DRY TENSILE STRENGTH



DRY (HZ / STAPLE)	
Max Load	11.21 lbs
Average Load	9.03 lbs
Min Load	5.90 lbs
Average Stress	8.49 psi
Standar Dev.	1.64 lbs



WET TENSILE STRENGTH

WET (HZ / STAPE)		
Sample	Load (lbs)	σ psi
1	4.57	1.614
2	6.29	2.221
3	5.2	1.836
4	3.29	1.162
5	2.82	0.996
6	4.41	1.557
7	5.61	1.981
8	5.36	1.893
9	4.9	1.730
10	7.87	2.779
11	7.68	2.712
12	5.79	2.044
13	6.29	2.221
14	6.3	2.225
15	5.98	2.112

WET (HZ / STAPE)	
Max Load	7.87 lbs
Average Load	5.49 lbs
Min Load	2.82 lbs
Average Stress	5.46 psi
Standar Dev.	1.44 lbs

PARTS WET FOR AN HOUR FROM 1:00 TO 2:30

Tensile strength test performed with dry straps.

Results where the staple was the failure. (The staple unbent out of the strap.)

The purpose of a catalog is to sell products or services to a targeted audience, or to advertise upcoming classes or events. Catalogs can be a great way to market your products or services, and also build your organization's identity.

Tensile strength test performed with wet straps.

Results where the staple was the failure. (The staple tore out of the strap.)

Wet tensile testing was performed with the straps after being submerged under water for 1 hour

STARTING, MID-SEASON AND END OF SEASON



DAMAGE, SCARRING, GIRDLING WITH WIRE, TWINE, ROPE AND VINYL TAPE



AFTER SEASON ENDS WITH SS11E





THANK YOU



SALES@CINCHSTRIP.COM

GM@CINCHSTRIP.COM



WWW.BOAFANG.COM